TECHNICAL DATA SHEET

Berolina-Liner

TECHNICAL DATA

Approved for UP and VE resins

- **Density after curing (ASTM D1505)**
  93.6 lb/ft³ (±31.2 lb/ft³)
- **Glass fibre content (EN ISO 1172 / by mass)**
  46% (± 8%)
- **Glass weight per unit area (per mm wall thickness)**
  19.2 oz/yd² (+4.4 / -3.0 oz/yd)
- **Short-term circumferential modulus of elasticity (ASTM D2412)**
  1,450,000 psi
- **Short-term modulus of elasticity in flexure (ASTM D790)**
  ≥ 1,450,000 psi
- **Short-term flexural strength (ASTM D790)***
  ≥ 150 N/mm²
- **Reduction factor for long-term values (ASTM D5365)**
  A = 1.45
- **Long-term circumferential modulus of elasticity (ASTM D2412)**
  ≥ 986,000 psi
- **Long-term flexural strength (ASTM D790)***
  ≥ 15,200 psi
- **Laminate Design**
  Multi-layer, seamless and overlapping in longitudinal direction; overlaps are offset
- **Linear expansion during calibration**
  ~ 0.0%
- **Allowable diameter tolerances of the host pipes**
  DIA ≤ 32 in. ± 5%; DIA > 32 in. ± 2%



UV GRP Liner for Gravity Sewer Applications

DESCRIPTION

BeroLina Liner features advanced glass-fiber reinforcement, for exceptional structural strength with minimal wall thickness. This minimizes loss of pipe diameter while maximizing the load-bearing capacity of the rehabilitated system.

AREAS OF APPLICATION

- Circular profiles: ID 6 - 38”
- Ovoid cross-sections: 8” / 12” - 28” / 41”

FEATURES & BENEFITS

- Seamless design, particular expandability
- Up to 1,640 / 3,280 ft. (≤ 12 in.)
- Can be stored up to 6 months (VE liners) or 12 months (UP liners)
- Fast curing and smooth surface
- Suitable for all standard pipe profiles
- Quality management in accordance with EN ISO 9001:2015
- Bridging small profile and cross-section changes
- Resin types depending on requirement (polyester, vinyl ester, styrene-free)
- Abrasion protection layer

ADDITIONAL INTEGRATED ENHANCED SECURITY ADVANTAGES

- Can be a substitute for gliding foil, reducing installation time
- Available up to 24”

APPROVALS

- DIBt Z-42.3-336 (UP and VE resins)
- WRc PT/496/0422 (UP and VE resin)
- CSTB 17.2/15-303_V4 (UP resins)
- City of Los Angeles, USA (UP resins)

+49 (0) 3304 20 88-100 | info@bkp-berolina.de | www.bkp-berolina.de



REINFORCEMENT MATERIAL

- Woven glass complex E-CR according to ASTM D578

RESINS

- **Unsaturated polyester resins (UP resins)**
  Type 1140 according to DIN 16946-2
  Group 3 according to DIN 18820-1
  Group 4 according to EN 13121-1
- **Vinyl ester resins (VE resins)**
  Type 1310 according to DIN 16946-2
  Group 5 according to DIN 18820-1
  Group 7 B according to EN 13121-1
- **Styrene-free resin**